



Application of Bona Sportive Paint and Finish

**directly after the installation of new pre-finished
Karelia Spring Sports Floors**

Application of Bona Sportive Paint and Finish

Directly after installation of the Karelia Spring Sport Floor

First lightly sand the UV-finish and carefully clean it to remove dust, etc. Use the Bona Scrad System, sanding disc, screen or sandpaper grade no. 150 or finer. Courts and lines should be marked with suitable lining tape pressed firmly to the floor.

Application of Bona Sportive paint

Stir the Bona Sportive paint thoroughly prior to use.

Apply the paint evenly using a suitable roller or brush for waterborne paint. Poor coverage will affect the opacity/hiding ability. Dual applications may be needed in some circumstances. N.B. The room and finish temperature must not fall below +13°C during application or drying. Remove the lining tape directly after application.

After the Bona Sportive Paint has dried thoroughly it should be lightly sanded using a Bona Scrad Pad (no wing) to provide a physical key for subsequent applications of finish. An application of Bona Sportive Finish may usually be made 24 hours after the paint has dried. If applying crossing lines, the paint may be crosspainted after minimum 1 hour.

Application of Bona Sportive finish

Ensure that the container is shaken thoroughly prior to use (or before decanting smaller quantities). The finish container and Bona Sportive Hardener are both provided with a measurement scale. After having determined the quantity of finish required add Sportive Hardener (4%) and either shake the container or stir it

carefully at once. Wait for 5 minutes before using, the mixed product must be used within 8 hours.

Application should be carried out using a Bona Roller or Bona Applicator Bar. Apply the finish evenly with a smooth flowing action avoiding accumulations of finish. N.B. The room and finish temperature must not fall below +13°C during application or drying.

Application rate: 8-10 m²/litre (120-100 g/m²) per coat.

Overcoating: 1-2 x Bona Sportive Finish

Drying time: 2½ - 3 hours per coat at 20°C/60% RH.

The floor will take light foot traffic approximately 8 hours after the final application and may be put into full use after 72 hours. After approx. 1 week the finish will be completely cured. The floor can then be cleaned normally. During the curing period it is suggested that dry cleaning methods is carried out.

N.B. It is essential that adequate ventilation be maintained during, and for one week after, application.