



Application of Bona Sportive Products to an old pre-finished Karelia Spring Sport Floor

Application of Bona Sportive Paint followed by Bona Sportive Finish

Surface preparation

The Bona Sportive Paint & Finish usually has good adhesion to old pre-finished Karelia Spring Sport Floor but the intercoat adhesion must always be checked prior to overcoating: Prepare a small area in an inconspicuous corner using Prep and a fine abrasive. Don't overdo it since that may give misleading results. Apply a coat of Bona Sportive Finish, after 3 days scratch the floor surface gently with a coin. If the finish stays firmly attached to the surface, the adhesion is satisfactory.

The surface which is to be coated must be completely clean. Floors which have been previously treated with wax, polish or similar products can not be overcoated.

When everything above is checked and ok, then prior to application, the floor must be treated with the Bona Prep system according to the instructions on the Prep label, using the Bona Scrad System, sanding disc/screen or sandpaper grade no. 150.

Application of Bona Sportive paint

Stir Bona Sportive paint thoroughly prior to use.

Apply the paint evenly using a suitable roller or brush for waterborne paint. Poor coverage will affect the opacity/hiding ability. Dual applications may be needed in some circumstances. N.B. The room and finish temperature must not fall below +13°C during application or drying. Remove the lining tape directly after application.

After the Bona Sportive Paint has dried thoroughly it should be lightly sanded using a Bona Scrad Pad (no wing) to provide a physical key for subsequent applications of finish. An application of Bona Sportive Finish may usually be made 24 hours after the

paint has dried. If applying crossing lines, the paint may be crosspainted after minimum 1 hour.

Application of Bona Sportive finish

Ensure that the container is shaken thoroughly prior to use (or before decanting smaller quantities). The finish container and Bona Sportive Hardener are both provided with a measurement scale. After having determined the quantity of finish required add Sportive Hardener (4%) and either shake the container or stir it carefully at once. Wait for 5 minutes before using, the mixed product must be used within 8 hours.

Application should be carried out using a Bona Roller or Bona Applicator Bar. Apply the finish evenly with a smooth flowing action avoiding accumulations of finish. N.B. The room and finish temperature must not fall below +13°C during application or drying.

Application rate: 8-10 m²/litre (120-100 g/m²) per coat.

Overcoating: 1-2 x Bona Sportive Finish

Drying time: 2½ - 3 hours per coat at 20°C/60% RH.

The floor will take light foot traffic approximately 8 hours after the final application and may be put into full use after 72 hours. After approx. 1 week the finish will be completely cured. The floor can then be cleaned normally. During the curing period it is suggested that dry cleaning methods is carried out.

N.B. It is essential that adequate ventilation be maintained during, and for one week after, application.